



Altius Minerals Corporation has a royalty interest in the Voisey's Bay Ni-Cu-Co deposit in Labrador, Canada, which is expected to commence production next month.

Altius also has exposure to gold, base metals, and uranium through a focused exploration portfolio that is largely funded by senior joint venture partners.

**Altius Minerals Corporation  
(ALS:TSXV)**

**Telephone 709.576.3440  
Toll Free 1.877.576.2209**

*[www.altiusminerals.com](http://www.altiusminerals.com)*

## Rambler Project Quality Control Information

Exploration on the Rambler property is being conducted by Altius Resources Inc. under a service agreement with Rambler Metals and Mining plc.

All drill holes have produced 47.6 millimetre diameter (1.875-inch) NO diamond drill core. The drill core is descriptively logged on site, aligned, marked for sampling and then split in half, longitudinally, using a diamond saw blade. One-half of the core is preserved in core boxes for future reference. The samples comprising the other half of the core are bagged, sealed and delivered directly to the analytical laboratory by Altius personnel. Base metal-bearing samples are nominally 1 metre to 1.8 metres (3.28 to 5.90 feet) in length except where specific geologic parameters require that a smaller interval be sampled. Samples with suspected precious metal content are nominally one metre or less, depending on the geological circumstances.

The sawed samples are delivered directly to Eastern Analytical Ltd. in Springdale, Newfoundland by Altius personnel where they are dried, crushed and pulped. Samples are crushed to approximately -10 mesh and split using a riffle splitter to approximately 300 grams. The sample split is pulverized using a ring mill to approximately 98% minus 150 mesh. In addition to regular samples, blank samples and quarter-split samples are also submitted for crushing/pulping.

The sample pulps are picked up directly at Eastern Analytical by Altius personnel and returned to the project site at which point analytical standard samples and duplicate samples from previous batches are inserted into the sample stream. All sample rejects are also retrieved from Eastern Analytical by Altius personnel and securely stored by Altius.

The sample pulps are shipped by courier to Activation Laboratories Ltd. in Ancaster, Ontario for analysis. A typical analysis consists of three, industry-standard components:

- (1) an aqua regia digestion followed by a 34 element ICP analysis,
- (2) a gold assay consisting of a one assay ton fire assay with finish by atomic absorption, and
- (3) an assay of specific base metals by aqua regia digestion followed by atomic absorption spectroscopy for those elements which exceed the limits of ICP accuracy.

Check assays for the Rambler project are being conducted by ALS Chemex, using industry-standard techniques posted on their website.

The drill program and sampling protocol are being supervised by J.Geoffrey Thurlow, Ph.D., P.Geo., of VMS Consultants Inc. and a Director of Altius; a Qualified Person as defined under the Canadian Securities Administrators' National Instrument 43-101.